

This is an abbreviated guide and is not intended as a substitute for the Long Form ISOLATEK® Type 400 AC & 400 ES Application & Installation Manual. Applicator shall completely and fully read and understand the Long Form Application & Installation Manual prior to applying this product.

PUMP REQUIREMENTS: Mechanical Piston, Hydraulic Piston or Rotor Stator type, open throat, screw feed pump with minimum “No. 4” soft rubber stators must be used.

MIXER REQUIREMENTS: Paddle or ribbon-type mortar mixer with safety cover and provision for quick dumping of mix directly into the pump hopper. Mixers capable of operating speeds of 35 to 40 RPM, are required. *Note: Continuous mixers may be used but a decrease in yield may occur. Mixers operating at less than required operating speeds may result in short “pot life”.*

WATER REQUIREMENTS: One bag of product requires 27 to 33 L (7.25 to 8.75 US Gallons) of potable water per bag. **A calibrated water meter is required** to ensure constant water volume per mix. *Note: The “five gallon bucket” method is unacceptable.*

MIX TIME: Product is mixed by first adding potable water to the mixer and then product. Mix for two (2) minutes to achieve the target mixer slurry density. **In a multiple bag mix, the mix time begins after the last bag has been added to the mixer. Do not mix more material than can be used in 30 minutes.**

HOSE SET-UP: High pressure plaster type hose. Typical Inner diameters (ID) and lengths are listed below.

<u>Total Hose Length</u>	<u>Diameter (ID)</u>	<u>Max. Length</u>
107 m (350 feet)	76 mm (3 in)	@ 15 m (50 ft)
	51 mm (2 in)	@ 61 m (200 ft)
	38 mm (1-1/2 in)	@ 15 m (50 ft)
	32 mm (1-1/4 in)	@ 8 m (25 ft)
	25 mm (1 in)	@ 8 m (25 ft)

Flexible hose length shall not exceed 107 m (350 ft.). Hose couplings shall be pressure rated victaulic screw-on type that does not restrict product flow. Steel tapered reducers must be used when a reduction in hose is necessary. Brass or aluminum couplings or reducers must not be used.

Metal standpipe 51 mm (2 in.) to 76 mm (3 in.) I.D. must be used when pumping height exceeds 5 stories or 18 m (60 ft.) or when total length (horizontal plus vertical) of material hose exceeds 107 m (350 ft.). Aluminum standpipe must not be used.

NOZZLE REQUIREMENTS: The spray nozzle assembly must consist of a min. 25 mm (1 in.) I.D. aluminum pole with a blow-off type nozzle cap. Nozzle orifice shall be nominal 13 mm (1/2 in.) I.D.

INTRODUCTION OF QWIK-SET: **ISOLATEK® QWIK-SET is required.** Typically introduced in-line. The QWIK-SET should be introduced max. 8 m (25 ft.) back from the nozzle; As an alternative, QWIK-SET can be introduced at the nozzle. Refer to ISOLATEK QWIK-SET Short Form Application Guide for further information. **Note: QWIK-SET mix ratio is 1 bag of QWIK-SET to 114 L (30 US Gallons) of water.**

NOZZLE DISTANCE: The distance between the nozzle and substrate will vary according to the type of equipment and nozzle used but must be between 305 mm (12 in.) and 610 mm (24 in.).

NOZZLE AIR PRESSURE: Use the amount of air at the nozzle that results in an even thickness build, texture and proper density. Excessive air will decrease yield. Optimal air pressure is 206.8.kPa (30 psi) as measured at the nozzle.

THICKNESS PER PASS: Apply 10 mm (3/8 in.) to 13 mm (1/2 in.) on the first pass, 19 mm (3/4 in.) to 25 mm (1 in.) on subsequent passes. **Note: Do not apply more than 38 mm (1-1/2 in.) of product in a 24 hour period. These are final expanded (accelerated) thicknesses.**

APPLICATION TEMPERATURE: A minimum substrate and ambient temperature of 4°C (40°F) shall be maintained prior to, during and a minimum of 24 hours after the application.

SURFACE PREPARATION: Ensure surfaces are clean and free of dirt, oil, grease, loose mill scale, paints/primers (other than those approved by Isolatek) and any other materials that may impair adhesion. For applications to primed steel, contact Isolatek Technical Services Department. **Note: Some substrates require the use of ISOLATEK Type EBS (adhesive), ISOLATEK Type PC, or metal lath. Refer to the ISOLATEK Type 400 AC & 400 ES Application & Installation Manual for specific requirements.**

SET-TIME:

ISOLATEK Type 400 AC sets in approximately 10 to 20 minutes depending on temperature and humidity conditions. Do not re-temper the product after it sets. See ISOLATEK QWIK-SET Short Form Application Guide for further information.

VENTILATION:

Provide a minimum of 4 complete air exchanges per hour until the material is dry.

SAFETY PRECAUTIONS:

ISOLATEK Type 400 AC is slippery when mixed with water. Do not allow wet material to remain on scaffolds, ladder rungs or floors. Walking on wet material may result in slips or falls. Signage must be posted in areas where the spray application of ISOLATEK Type 400 AC is ongoing to warn other trades of slip hazards.

CALCULATING MIXER DENSITIES:

1. Weigh an empty 1036cc cup and tare the scale to account for the cup weight.
2. Fill the cup with material from the pump hopper. Then gently tap the cup on a hard surface to eliminate all air pockets.
3. Level the material with top of cup.
4. Weigh the filled cup in grams.
5. Compare weight in grams to the mixer density in chart below.

ESTIMATING ISOLATEK TYPE 400 AC MIXER DENSITY FROM WET CUP WEIGHTS

WET CUP WEIGHT (Grams)	MIXER DENSITY Using 30 L (8.0 US Gals) Water	
	PCF	(kg/m ³)
797	48.0	(769)
805	48.5	(777)
814	49.0	(785)
822	49.5	(793)
830	50.0	(801)
838	50.5	(809)

Cup Size = 1036 cc

CALCULATING NOZZLE DENSITIES:

(Estimating Yield/Bag from Nozzle Wet Cup Weights)

- 1.
2. Weigh an empty 1036cc cup and tare the scale to account for the cup weight.
3. While the pump and atomizing air are running, place the nozzle inside cup and slowly pull back as the cup fills.
4. Level ISOLATEK Type 400 AC with the top of cup, being careful not to compress the ISOLATEK Type 400 AC. Leveling should be repeated until the material stops swelling in cup. When leveling the ISOLATEK Type 400 AC, angle the spatula so that it is cutting the excess material as opposed to troweling/compressing it.
5. Weigh the filled cup in grams.
6. Using the chart below, determine the corresponding density and yield based on the water usage rate and the weight of the cup.
7. Adjust the QWIK-SET flow rate and repeat the steps above until the desired density and yield are achieved.

27 L (7.25 gal)/bag Nozzle Cup weight in grams (Net mat'l wt)	28 L (7.5 gal)/bag Nozzle Cup weight in grams (Net mat'l wt)	29 L (7.75 gal)/bag Nozzle Cup weight in grams (Net mat'l wt)	30 L (8.0 gal)/bag Nozzle Cup weight in grams (Net mat'l wt)	31 L (8.25 gal)/bag Nozzle Cup weight in grams (Net mat'l wt)	32 L (8.5 gal)/bag Nozzle Cup weight in grams (Net mat'l wt)	DRY DENSITY (Estimated) PCF (kg/m ³)	YIELD Est. Gross Yield/Bag Bd. ft. (m ² @1 mm)
715	729	742	755	769	782	22 (352)	31 (74)
748	762	776	790	804	818	23 (368)	30 (70)
780	795	810	824	839	853	24 (384)	29 (67)
813	828	843	858	874	889	25 (400)	27 (65)

Note: If you are having difficulty achieving these nozzle cup weights, please contact the Isolatek International Technical Service Department for assistance.

* Nozzle weights are based on a cup with a volume of 1036cc.

Note: UL minimum average density for ISOLATEK Type 400 AC is 352 kg/m³ (22 pcf) and the minimum individual density is 304 kg/m³ (19 pcf).

NOTE: Only the listed equipment, nozzles and procedures are approved for applying ISOLATEK Type 400 AC. Deviations from these requirements will result in product not meeting claims as published in the literature. **For additional information, please contact the Technical Service Department.**